



TEST REPORT NO:097452

Date:10 December 2014

PROQUINAL S.A.
PBX (571) 2417800
CALLE 11 # 34-50.
BOGOTA D.C
COLUMBIA
COLOMBIA

The following sample(s) was/were submitted and identified by/on behalf of the client as:

Retailer

Description of article

Retailer style number Retailer Standard Number

Order No./ Buyer

Quality/Fibre Composition

Date Sample(s) Received:

Not Specified

5789 Valencia

- ABS

Unknown

CATALINA SARAY ALBA

Unknown

02 December 2014

Test

BS5852 Annex E, Water Soak BS5852 Ignition Source 5 (cribs)

Remarks

Tests as requested by the customer

Signature

Quey Peberdy Technologist

For and on behalf of SGS Leicester Ltd.

All samples are conditioned to ISO 139 where conditioning is required (unless otherwise stated)

This document is issued by the Company under its General Conditions of Service accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law." Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 90 days only





Customer:

Proguinal S.A.

Test Report No:

097452

BS 5852:2006: Clause 11: Ignition Source 5

Test Request

The sample supplied is a PVC coated fabric and has been tested to BS 5852:2006 Clause 11 using Ignition Source 5.

Fibre Identification

Reputed Fibre Composition: Unknown

Pre-Treatment:

The sample supplied was water soaked and dry in accordance to BS 5852:2006 Annex E

Conditioning:

Before testing the sample was conditioned in an indoor ambient condition for 72 hours and in a standard atmosphere having a temperature of $20^{\circ}\text{C} \pm 5^{\circ}\text{C}$ and a relative humidity of 50% r.h \pm 20% for a minimum of 16hours.

Comments on Test Results

The sample supplied meets the requirements of BS 5852:2006 Clause 11, NI/5.

Results

"The following test results relate only to the ignitability of combination of upholstery composites (BS 5852:2006 Clause 11) under the particular conditions of the test stated; they are not intended as a means of assessing the full potential fire hazard of the materials or products in use."

Ignition Source 5

Pass Criteria: ~ Disregard flaming which ceases within 10 minutes. Smoke, heat or glowing which ceases within 60 minutes of igniting the crib.

No smouldering is to be present in the final examination.

Specimen Number	1	Time	2	Time
Smoking	Y	5mins 52secs	Y	5mins 29secs
Smouldering	N		N	
Flaming	Y	4mins 17secs	Y	4mins 38secs
Afterglow	N		N	-
Flame front reaches extremities within the test duration (other than the top of vertical part)	N		N	
Cover Split	Y	12	Y	*
Final examination (ignition or Non-Ignition)	Non ignition		Non ignition	

Please note that the fabric sample was tested over combustion modified foam with a density of 35kg per M3.

Key: Y = Yes

N = No

N/A = Not Applicable

End of Report

This document is issued by the Company under its General Conditions of Service accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company, Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law." Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 90 days only